



Product Description

Evero Geo Series is a natural quartz surface made from a blend of bio-based resin, natural quartz and other exotic minerals. It is made of 20% recycled content.

Evero Pearl Series is a natural quartz surface made with bio-based resin, sea shells and natural quartz. It is made of 60% recycled content.

- Variations in the natural stone color, pattern, size, shape and shade are inherent. Due to these unique characteristics, please expect subtle shade variations when units are installed adjacent to each other.

Evero features a 15 year warranty.

Product Qualities

- Available in a variety of colors
- Durable, long-lasting material
- Smooth, non-porous surface
- Easy to clean and maintain, absence of cracks or crevices prevent bacteria and mold from accumulating
- Chemical, stain, impact and scratch resistant
- Repairable
- Homogenous composition allows for even distribution of color throughout material
- UV light resistant
- Available in shaped products

Care and Maintenance of Engineered Quartz

- For regular cleaning use mild neutral base cleaners.
- Remove tough stains with non abrasive cleaners and pads such as a white Scotch Brite® or an eraser sponge.
- Avoid contact with harsh chemicals such as paint remover, bleach, acetone, chloride based cleaners, floor cleaners, etc.
- To optimize material performance it is recommended to apply DryTreat Stain-Proof Original or equivalent. Apply annually or as needed.

Additional product literature available at bradleycorp.com.

- Use of brand names is intended only to indicate a type of product. This does not constitute an endorsement. Nor does the omission of any brand name imply its inadequacy.
- All products should be used in strict accordance with package instructions.

Physical Properties

Physical Properties	Average Test Result	Test Method
Coefficient of Thermal Expansion	26.28 ppm/°C	ASTM C-531
Flexural Strength	3178.5 psi	ASTM D790
Flexural Modulus	2086 ksi	ASTM D790
Compressive Strength	12,645 psi	ASTM C170
Moisture Absorption	0.1125 % 24 hours	ASTM D570
Hardness	6-7	Mohs Scale
Gloss (60)	40% minimum	Glossmeter
Fire Resistance, Flame & Smoke*	Class 1	ASTM E84
Density	2.14 g/cm3	ASTM C97

*Geo Series only

ANSI Standards

Physical Properties	ANSI Test	Results
Surface Integrity	3.3	Pass
Strength of Drain Connection	4.2	Pass
Impact Resistance	4.3	Pass
Load Resistance	4.4	Pass
Colorfastness	5.1	Pass
Stain Resistance	5.2	Pass
Chemical Resistance	5.5	Pass
Thermal Shock	5.6	Pass
Wear and Cleanability	5.3	Pass

