

Your composition:

4 mm Sunergy Clear pos.2

Personal notes:

LIGHT

Transmission	69
Reflection	9

ENERGY

Solar factor	61
Reflection	10



LIGHT PROPERTIES (EN 410)

EN 410

Light Transmission - τ_v (%)	69
Light Reflection - ρ_v (%)	9
Internal light reflection - ρ_{vi} (%)	10
Colour Rendering - RD65 - Ra (%)	98

ENERGY PROPERTIES

EN 410

ISO 9050

Solar factor - g (%)	61	60
Energy Reflection - ρ_e (%)	10	11
Direct Energy Transmission - τ_e (%)	56	53
Total Energy absorption - α_e (%)	34	36
Shading coefficient - SC	0.7	0.69
UV Transmission - UV (%)	44	
Selectivity	1.13	1.13

OTHER PROPERTIES

Resistance to fire - EN 13501-2	NPD
Reaction to fire - EN 13501-1	A1
Bullet Resistance - EN 1063	NPD
Burglar Resistance - EN 356	NPD
Pendulum body impact resistance - EN 12600	NPD
Direct airborne sound insulation (R_w (C;Ctr) - EN 12758) - dB	30 (-2; -4) ⁽¹⁾

THERMAL PROPERTIES (EN 673)

EN 673

Ug-Value - $W/(m^2.K)$	4.1
------------------------	-----

THICKNESS AND WEIGHT

Nominal thickness (mm)	4
Weight (kg/m^2)	10.0

The data are calculated using spectral measurements that are conform to standards EN 410, ISO 9050 (1990) and WIS/WINDAT.

The Ug-value (formerly k-value) is calculated according to standard EN 673. The emissivity measurement complies with standards EN 673 (Annex A) and EN 12898.

This document is no evaluation of the risk of glass breakage due to thermal stress. For tempered glass: the risk of spontaneous breakage due to Nickel-Sulfide is not covered by AGC Glass Europe. The Heat Soak Test is available on request.

Specifications, technical and other data are based on information available at the time of preparation of this document and are subject to change without notice. AGC Glass Europe can not be held responsible for any deviation between the data introduced and the conditions on site. This document is only informative, in no way it implies an acceptance of the order by AGC Glass Europe.

See also conditions of use.

⁽¹⁾These sound reduction indexes correspond to glazings which are 1,23 by 1,48m according to EN ISO 10140-3 and are tested in laboratory conditions. In-situ performances may vary according to the effective glazing dimensions, frame system, noise sources etc. The accuracy of the given indexes is not better than +/- 1dB.

⁽²⁾These sound reduction indexes are estimated (no test). They correspond to glazings which are 1,23m. by 1,48 m. In-situ performances may vary according to the effective glazing dimensions, frame system, noise sources etc. The accuracy of the given indexes is +/- 2dB.